COLD HEADING WIRE

INTRODUCTION

Cold heading wire is mainly used for various kinds of fasteners and pins for construction & automotive use as well as precision disc use. It has excellent corrosion resistance and mechanical properties depending on the grades. In order to obtain good- shaped upsetting and threading it is very essential to select the most suitable grades with highest quality.

LUBRICATION COATING

If required by customers, we can coat the wire with a special thin film which provides excellent lubrication for cold heading and also provides threadability including forward & backward browing, longer tool life with less clogging and easier cleaning.

CHARACTERISTICS

High formability Low working stress Excellent surface quality Most proper hardenability and low tool wearing Superior low magnetism after heading & threading

PRODUCT GRADE





CHART FOR MECHANICAL PROPEWRTIES



鋼種 Product Grade				,	化學成份	Chemical Composition(%)				
KT	AISI	SUS	С	Si	Mn	Р	S	Ni	Cr	Other
K304	304	304	≦0.08	≦1.00	≦2.00	≦0.045	≦0.030	8.00-10.50	18.00-20.00	-
K304Cu	304Cu	XM-7	≦0.08	≦1.00	≦2.00	≦0.045	≦0.030	8.00-10.50	17.00-19.00	Cu:3.00-4.00
K304HC	-	(304J3)	≦0.08	≦1.00	≦2.00	≦0.045	≦0.030	8.00-9.00	18.00-19.00	Cu:2.00-3.00
K305j1	(305)	305J1	≦0.08	≦1.00	≦2.00	≦0.045	≦0.030	11.00-13.50	16.50-19.00	-
K316	316	316	≦0.08	≦1.00	≦2.00	≦0.045	≦0.030	10.00-14.00	16.00-18.00	Mo:2.00-3.00
K316Cu	-		≦0.03	≦1.00	≦2.00	≦0.040	≦0.030	10.50-13.50	16.00-18.00	Cu:2.80-3.80 Mo:2.00-3.00
K430	430	430	≦0.12	≦0.75	≦1.00	≦0.040	≦0.030	-	16.00-18.00	-



KUANG TAI METAL INDUSTRIAL CO., LTD. No. 20, Kung Yeh Rd, Erh Chen Tsun, Kuan Tien Hsiang, Tainan Hsien, Taiwan Tel: 886-6-6987615 Fax: 886-6-6987315