| Flux Cored Wire for Stainless Steel | | | | | | | |
|-------------------------------------|--|----------------|---------|---------------------|--|--|--|
| | | Classification | | | | | |
| KFW-309LMoF | | AWS | A5.22 | E309LMoT0-1/4 | | | |
| | | JIS | Z3321 | TS309LMo-FB0 | | | |
| | | EN | 17633-A | T 23 122L RC1/M21 2 | | | |
| Shielding Gas: | CO ₂ or Ar+20%CO ₂ | GB | T 17853 | E309LMoT0-1/4 | | | |

Applications and Features

(1) Weld metal contains Mo and low carbon contents, which provide superior corrosion resistance.

(2) It is suitable for joining stainless steel to carbon steel or low alloy steel.

(3) It has bright silvery appearance and good wettability.

Welding Position

F (IG), H-Fillet (2F)

Welding Instruction

(1) For welding dissimilar metals, please refer to Appendix I.

(2) For other instructions, please refer to Appendix D.

(3) For extra information, please refer to Appendix F.

| Typical Chemical Composition of Weld Metal (wt %) (Shielding Gas : CO ₂) | | | | | | |
|--|------|------|-------|-------|-------|-------|
| С | Si | Mn | Р | S | Cr | Ni |
| 0.037 | 0.63 | 1.81 | 0.031 | 0.006 | 23.60 | 12.32 |

Typical Mechanical Properties of Weld Metal (Shielding Gas : CO₂)

| Tensile Strength | Elongation |
|--|------------|
| N/mm ² (kgf/mm ²) | % |
| 590(60.2) | 34 |

Size and Suggested Operating Range (DC+)

| | F/H-f | illet | V/OH | | |
|---------------|---------|-------|---------|-------|--|
| Diameter (mm) | Amp | Volt | Amp | Volt | |
| 1.2 | 100~300 | 20~36 | 100~200 | 24~30 | |
| 1.6 | 200~360 | 26~40 | — | — | |